



Standard Specification for Raw and Burnt Sienna Pigments¹

This standard is issued under the fixed designation D 765; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the pigments commercially known as raw sienna and burnt sienna.

2. Referenced Documents

2.1 ASTM Standards:

D 50 Test Methods for Chemical Analysis of Yellow, Orange, Red, and Brown Pigments Containing Iron and Manganese²

D 185 Test Methods for Coarse Particles in Pigments, Pastes, and Paints²

D 280 Test Methods of Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments²

D 387 Test Method for Color and Strength of Chromatic Pigments with a Mechanical Muller³

D 1208 Test Methods for Common Properties of Certain Pigments³

3. Composition and Properties

3.1 *Dry Pigments*—The pigments shall conform to the following requirements:

3.1.1 *Raw Sienna*—The pigment shall be in a soft, dry form and shall be a hydrated oxide of iron permeating a siliceous base. The pigment shall conform to the requirements for composition prescribed in Table 1.

3.1.2 *Burnt Sienna*—The pigment shall be produced by the calcination of raw sienna and shall conform to the requirements for composition prescribed in Table 1.

3.2 *Paste in Oil*—For both raw and burnt sienna, the paste in oil shall be made by thoroughly grinding the pigment with linseed oil (with or without a small amount of volatile thinner) together with (where necessary) small amounts of wetting or dispersing agents to produce a paste or semipaste of satisfactory consistency. As received, it shall not be caked in the container and shall break up readily in linseed oil to form a smooth paint of brushing consistency. It shall mix readily in all

TABLE 1 Requirements for Composition of Raw and Burnt Sienna

	Raw Sienna	Burnt Sienna
Iron oxide (Fe ₂ O ₂), min, %	38	40
Calcium compounds (as CaO) max, %	5.0	5.0
Moisture and other volatile matter, max, %	4.0	4.0
Coarse particles (total residue retained on a No. 325 (45- μ m) sieve), max, %	2.0	2.0
Organic colors, max, %	none	none

proportions, without curdling, with linseed oil, turpentine, or volatile petroleum spirits, or any mixture of these substances. The paste shall conform to the following requirements:

Pigment, min, %	60
Nonvolatile vehicle, min, of vehicle	80
Moisture by distillation, max, %	2.0
Coarse particles and skins (total residue retained on a No. 325 (45- μ m) sieve), max, % of dry pigment	1.0

3.3 The mass color and character of the tint and the tinting strength formed by a mixture with a white pigment shall be within mutually agreed upon limits of a standard acceptable to both the purchaser and the seller.

4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear, samples shall be taken from different packages in the ratio of two samples for each 5 tons (inch-pound or SI), except that for shipments of less than 10 000 lb two samples shall be taken. At the option of the purchaser, the samples may be tested separately or after blending in equal quantities the samples from the same production unit to form a composite sample.

5. Test Methods

5.1 Tests shall be conducted in accordance with the appropriate ASTM test methods. Test procedures not covered by ASTM test methods shall be mutually agreed upon by the purchaser and the seller.

5.1.1 *Total Iron Oxide, Calcium Compound, and Organic Coloring Matter*—Test Methods D 50.

5.1.2 *Coarse Particles*—Test Methods D 185.

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Oct. 1, 2003. Published October 2003. Originally approved in 1944. Last previous edition approved in 1987 as D 765 – 87 (1999).

² *Annual Book of ASTM Standards*, Vol 06.03.

³ *Annual Book of ASTM Standards*, Vol 06.01.

5.1.3 *Pigment and Linseed Oil in Paste in Oil*—Test Methods D 1208.

5.1.4 *Moisture in Paste in Oil*—Test Methods D 280, except that the sample shall be weighed instead of measured and the results shall be expressed as percentage by weight instead of volume.

5.1.5 *Mass Color and Tinting Strength*—Test Method D 387.

6. Keywords

6.1 burnt sienna; iron; manganese; pigment; raw sienna

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).